



Primer Marine

SABA, a strong bond

Description

SABA Primer Marine is a one-component primer. SABA Primer Marine is very suitable for priming teak deck parts that are to be sealed with SABA Sealer 211 C, SABA Seal One and SABA Seal One HM.

Solvent based adhesives

Special properties

- Very good resistance to water
- Applied primer is visible because of black colour
- Short drying time and long open time

MSP sealants

Method of use

Apply with a brush

Water based adhesives

Technical data

Silicone sealants

Base	: chlorine rubber
Viscosity at 23 °C	: approx. 50 mPa.s
Density	: approx. 1010 kg/m ³
Colour	: black
Solids content	: approx. 31%
Flash point	: below 32° C
Solvents	: n-butyl propionate
Open time	: 30 minutes - 20 hours
Drying time	: approx. 30 minutes
Coverage	: approx. 100 g/m ²
Clean tools with	: SABA Cleaner 21
Work temperature	: minimum +5 °C
Storage temperature	: minimum 5 °C, maximum +35 °C
Temperature resistance	: -30 °C up to +70 °C
Shelf life	: 18 months in unopened packing

Foam coatings

Hotmelts

Epoxy products

PU products

Polysulfide products

Order information

Packing	tin
Content	500 ml

Primers

Colour	black
Article No.	100672

Cleaning agents

Safety recommendations

See the corresponding material safety data sheet.



SABA Dinxperlo BV

Industriestraat 3, NL-7091 DC Dinxperlo, PO Box 3, NL-7090 AA Dinxperlo, the Netherlands, Tel +31 (0) 315 658999, Fax +31 (0) 315 653207, E-mail info@saba.nl, Internet www.saba.nl.

Our application instructions and technical advice are based on our actual level of knowledge. We cannot accept any liability for conclusions and recommendations resulting from these. Buyers and/or users should judge the suitability of our products for any envisaged application by preliminary testing. The general terms and conditions for the members of the "Nederlandse Vereniging van Rubber- en Kunststoffabrikanten (NVR)" apply on all our deliveries.

Version number: 200405